

ASPEN 350/84 MB



Pulp characteristics (indicative) TCF, Flash Dried									
Freeness	Brightness	Bulk	Bulk	Tensile Index	Opacity	Light Scattering	Shives Sommerville	Air resistance Gurley	pH
CSF ml	% ISO	cm ³ /g	cm ³ /g	Nm/g	% ISO	m ² /kg	% 0,15 slot	S	
ISO 5267	ISO 2470 ISO 3688	ISO 534 ISO 5269-2	ISO 534 / 5269-1 TAPPI T411	ISO 1924-2 ISO 5269-2	ISO 2471 ISO 5269-2	ISO 9416 ISO 5269-2	TAPPI T275	ISO 5636-5 ISO 5270	TAPPI T252
350 +/- 50	83,7 min 83	1,8	2,4	30	83,5	39	0,01	9	6,5-7,8

Main uses
Printing and writing papers
Coated and uncoated papers
Speciality papers

Certificates	
Quality system	ISO 9001:2015
Environmental management system	ISO 14001:2015
Health and Safety management system	OHSAS 18001:2007
Chain of custody / Controlled wood	PEFC COC or FSC COC/CW
Conformity with food contact materials	ISEGA 2792 U 09
Nordic Ecolabel (inspected pulp)	Valid from 19.03.2014

ASPEN 350/84 MB

Bale size (l x w x h in cm): 90 x 63 x 49	
Gross weight	ca. 223 kg (ca. 214,5 ADkg)
Bale wire	2 (galvanized) x Ø 2,3 mm
Wrapping	Bleached Kraft Paper 200 g/m ²
Markings	Brand name, bale number, company logo

Unit size (l x w x h in cm): 90 x 130 x 199	
Gross weight	ca. 1784 kg (ca. 1716 ADkg)
Unit wire	6 (galvanized wires) x Ø 3,0 mm
Unit	8 bales

